

Synthesis of Symmetrical and Unsymmetrical Triphenylene Discotic Liquid Crystals Using Antimony(V)Chloride Under Scholl Oxidation

Sandeep Kumar* and Srinivasa HT

Raman Research Institute, C.V. Raman Avenue, Sadashivanagar, Bangalore, India

Abstract

Triphenylene-based discotic liquid crystals, useful in studying the energy and charge migration in self-organized systems, are the most widely synthesized and studied discotic liquid crystals. In this paper, we report an efficient synthetic procedure for the preparation of symmetrical and unsymmetrical triphenylene discotic liquid crystals using antimony pentachloride as a novel reagent. Scholl oxidative trimerization of 1,2-dialkoxybenzenes with SbCl_5 yields hexaalkoxytriphenylenes in good yield, while the oxidative coupling of a 3,3',4,4'-tetraalkoxybiphenyl with a 1,2,3-trialkoxybenzene affords an unsymmetrically substituted heptaalkoxy-triphenylene derivative. The potential of this new reagent was compared with the other known reagents for the synthesis of alkoxytriphenylenes.

Keywords: Triphenylene; Discotic liquid crystal; Scholl reaction; Antimony pentachloride

Introduction

Despite its complicated nature, the Scholl reaction has been extensively used in organic synthesis [1-11]. In Scholl oxidation, a new C-C bond between two aryl moieties is generated under the influence of Friedel-Crafts catalyst. A Lewis acid and an oxidant is required to accomplish this reaction. Transition metal halides, such as, FeCl_3 , MoCl_5 , etc., which act both as Lewis acid and oxidant are often applied to achieve this condensation. Though this reaction was discovered more than a century ago [12], its mechanism is still under debate. Two possible reaction mechanisms, arenium cation mechanism [9] and radical cation mechanism [4], have been discussed in literature. Recently, the Scholl coupling has been well exploited in the synthesis of discotic liquid crystals (DLCs). DLCs are formed due to self-organization of disc-like molecules [13]. Depending upon the strength of molecular interactions, disc-like molecules can form nematic or columnar phases. The columnar phases formed by these molecules have been extensively studied for one-dimensional conducting properties and their applications in devices like, photovoltaic solar cells, light emitting diodes, sensors, thin film transistors, etc., have been sought. The chemistry and physics of DLCs have recently been reviewed in several research articles [14-31].

Since the discovery of DLCs, triphenylene-based DLCs remained the focal point of research in this field [32-37]. This is mainly because these materials are chemically and thermally stable, their chemistry is relatively easy and they show many different mesophases. Moreover, their one-dimensional conducting properties offer many potential applications. Accordingly, a large number of triphenylene (TP) discotics have so far been prepared to investigate their mesomorphic properties [15]. Hexaalkoxy-TPs are the most widely synthesized and studied discotic mesogens and a number of methods have been developed for their synthesis [34]. The synthesis of hexaalkoxy-TPs involves oxidative trimerization of 1,2-dialkoxybenzene which is one of the unusual cases of Scholl reaction where more than one aryl-aryl bonds are formed. 1,2-dimethoxybenzene (veratrole) was oxidatively trimerized using chloranil or FeCl_3 in concentrated H_2SO_4 at room temperature to obtain hexamethoxy-TP [38]. Initially TP discotics were prepared using this sluggish low yielding methodology but later the Leeds group developed an efficient methodology to prepare triphenylene hexaethers via oxidative trimerization of 1,2-dialkoxybenzene using FeCl_3 using

only a catalytic amount of H_2SO_4 (0.3%) in dichloromethane followed by a reductive work-up using methanol [39]. Previously we have reported two other reagents, molybdenum pentachloride [40] and vanadium oxytrichloride [41], to be highly efficient for the preparation of triphenylene hexaethers. Here we discovered yet another reagent, antimony pentachloride (SbCl_5), which can be efficiently used to prepare hexaalkoxy-TP in good yield. Antimony pentachloride is a strong Lewis acid and its application in Friedel-Crafts reaction is well documented [42]. However, its application as Scholl oxidant for the synthesis of triphenylene discotics has so far not been reported. Here we report the synthesis of symmetrical and unsymmetrical triphenylene discotics using this new reagent.

Experimental Section

In a typical reaction (Scheme 1), SbCl_5 (4.48 g, 0.015 mol) was added to a solution of 1,2-dibutoxybenzene (1.5 g, 0.0067 mol) in 15 ml of dry CH_2Cl_2 . The reaction mixture was stirred at room temperature for 30 min under anhydrous conditions. It was then poured over cold MeOH (50 ml), diluted with water (50 ml) and extracted with hexane (4x30 ml). The combined extracts were washed with water and brine, dried over anhydrous sodium sulphate, the solvent was removed under vacuum and the crude product was purified by column chromatography over silica gel, yielding 1.15 g (78%) of hexabutoxytriphenylene. All the symmetrical hexaalkoxy-triphenylenes were prepared in the same manner and their yield is reported in table 1. They were fully characterized from their spectral and elemental analysis. All the hexaalkoxy-TP exhibit similar ^1H NMR differing only in the aliphatic protons.

Typical ^1H NMR data for the compound **2a**: δ_{H} (CDCl_3) 7.83 (s, 6H),

*Corresponding author: Sandeep Kumar, Raman Research Institute, C.V. Raman Avenue, Sadashivanagar, Bangalore, India, Tel: +91 80 23610122; Fax: +91 80 23610492; E-mail: skumar@rri.res.in

Received March 22, 2013; Accepted April 15, 2013; Published April 22, 2013

Citation: Kumar S, Srinivasa HT (2013) Synthesis of Symmetrical and Unsymmetrical Triphenylene Discotic Liquid Crystals Using Antimony(V)Chloride Under Scholl Oxidation. Organic Chem Curr Res 2: 116. doi:10.4172/2161-0401.1000116



Copyright: © 2013 Kumar S, et al. This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.

4.23 (m, 12H), 1.94 (m, 12H), 1.6-1.3 (m, 12H), 0.9 (t, 18H). Elemental anal.: **2a**: calculated for $C_{42}H_{60}O_6$, C 76.33, H 9.15; found, C 76.45, H 8.94%; **2b**: calculated for $C_{48}H_{72}O_6$, C 77.38, H 9.74; found, C 77.62, H 9.44%; **2c**: calculated for $C_{54}H_{84}O_6$, C 78.21, H 10.21; found, C 78.4, H 10.44%. Thermal behaviour: **2a**: Cr 89.9 Col_p 145.6 I; **2b**: Cr 71.4 Col_h 121.5 I; **2c**: Cr 67.4 Col_h 100.0 I.

To prepare an unsymmetrical heptaalkoxy-TP derivative **5** (Scheme 2), $SbCl_5$ was added to a solution of 3,3',4,4'-tetrabutylxybiphenyl **3**, and 1,2,3-tributylxybenzene **4** in dichloromethane. Typical work-up give 1,2,3,6,7,10,11-heptabutylxy-TP **5** in about 25% yield (Table 1, entry 7). ¹H NMR: δ_H ($CDCl_3$) 9.2 (s, 1 H), 7.8 (s, 2 H), 7.8 (s, 1 H), 7.7 (s, 1 H), 4.2 (m, 12 H), 4.0 (t, 7.1, 2 H), 1.9 (m, 14 H), 1.6 (m, 14 H) and 1.0 (m, 21 H). Elemental anal.: **5**: calculated for $C_{46}H_{68}O_7$, C 75.37, H 9.35; found, C 75.0, H 9.44%. Thermal behaviour: Cr 65.5 Col 70.1 I.

Results and Discussion

The trimerization of 1,2-dialkoxybenzene to hexaalkoxy-TP is presented in Scheme 1. Addition of antimony pentachloride (2.5 equivalent) to a solution of 1,2-dialkoxybenzene in dichloromethane yields 2,3,6,7,10,11-hexaalkoxy-TPs in 30 min (Table 1). It has been reported that the addition of a catalytic amount of mineral acid improves yields in some cases [15,16]. However it is also known that Lewis acids can complex with mineral acids [4], reducing the effective amount of the oxidant and thus yield of the final product. Therefore, reactions were carried out under both conditions and results are collected in table 1. As can be seen from table 1, entry 2, addition of acid decreases the yield, indicating complex formation between the Lewis acid and mineral acid. Further, increasing the amount of $SbCl_5$ from 2.5 eq to 3.2 eq (Table 1, entry 4) does not increase the yield of final pure product probably due to the formation of other side products



Entry	Substrate	Oxidant (equivalent)	H ₂ SO ₄ (%)	Time (min)	Product	Yield
1	1a	$SbCl_5$ (2.5)	0.0	30	2a	78
2	1a	$SbCl_5$ (2.5)	0.3	30	2a	70
3	1a	$SbCl_5$ (2.5)	0.0	180	2a	70
4	1a	$SbCl_5$ (3.2)	0.0	30	2a	50
5	1b	$SbCl_5$ (2.5)	0.0	30	2b	55
6	1c	$SbCl_5$ (2.5)	0.0	30	2c	59
7	3 + 4	$SbCl_5$ (2.5)	0.0	30	5	25
8	1a	$FeCl_3$ (2.5)	0.3	30	2a	65
9	1a	$MoCl_5$ (2.5)	0.3	30	2a	74
10	1a	$VOCl_3$ (2.5)	0.3	30	2a	81

Table 1: Preparation of hexaalkoxy-TPs using $SbCl_5$ in CH_2Cl_2 solution.

at the expense of hexaalkoxy-TP. All the products were characterized from their spectral data, phase behaviour and a direct comparison with an authentic sample and found to be in full agreement with literature data [15].

To compare the potential of $SbCl_5$ with respect to other three Lewis acids viz, $FeCl_3$, $MoCl_5$ and $VOCl_3$, known for the synthesis of hexaalkoxy-TPs, reactions were carried out under identical conditions using 1,2-dibutylxybenzene as substrate (Table 1, entries 8-10). It may be noted that the optimised reaction conditions for different reagents could be different. Therefore, the best yield for various reagents could be different under optimised conditions. From the data, it is clear that under the one set of identical reaction conditions, $SbCl_5$ is slightly better than $FeCl_3$ but not the best reagent known in literature for this trimerization.

As reported for other reagents viz, $FeCl_3$, $MoCl_5$ and $VOCl_3$, this reagent can also be used for the synthesis of unsymmetrical TP, albeit in poor yield, under similar reaction conditions (Scheme 2). Thus, when 3,3',4,4'-tetrapentylxybiphenyl **3**, was coupled with a 1,2,3-trialkoxybenzene **4**, 1,2,3,6,7,10,11-heptabutylxy-TP **5** is formed in about 25% yield (Table 1, entry 7).

Conclusion

In conclusion, Antimony(V) chloride, a new reagent, was found to be useful in the synthesis of symmetrical and unsymmetrical alkoxy-triphenylene DLCs. The reagent may be explored for the synthesis of various other discotic liquid crystals involving inter- or intramolecular Scholl oxidation.

References

- Danz M, Tonner R, Hilt G (2012) Understanding the regioselectivity in Scholl reactions for the synthesis of oligoarenes. *Chem Commun (Camb)* 48: 377-379.
- Waldvogel SR, Trosien S (2012) Oxidative transformation of aryls using molybdenum pentachloride. *ChemCommun (Camb)* 48: 9109-9119.
- Pradhan A, Dechambenoit P, Bock H, Durola F (2011) Highly twisted arenes by Scholl cyclizations with unexpected regioselectivity. *Angew Chem Int Ed Engl* 50: 12582-12585.
- Zhai L, Shukla R, Wadumethrige SH, Rathore R (2010) Probing the arenium ion (protontransfer) versus the cation-radical (electron transfer) mechanism of Scholl reaction using DDQ as oxidant. *J Org Chem* 75: 4748-4760.
- Lu Y, Moore JS (2009) Semi-fused hexaphenylhexa-peri-hexabenzocoronene: a novel fluorophore from an intramolecular Scholl reaction. *Tet Lett* 50: 4071-4077.
- Sarhan AA, Bolm C (2009) Iron(III) chloride in oxidative C-C coupling reactions. *ChemSoc Rev* 38: 2730-2744.
- Nagarajan S, Barthes C, Gourdon A (2009) Cyclodehydrogenation of hetero-oligophenylenes. *Tetrahedron* 65: 3767-3772.

8. Dou X, Yang X, Bodwell GJ, Wagner M, Enkelmann V, et al. (2007) Unexpected phenyl group rearrangement during an intramolecular Scholl reaction leading to an alkoxy-substituted hexa-peri-hexabenzocoronene. *Org Lett* 9: 2485-2488.
9. King BT, Kroulák J, Robertson CR, Rempala P, Hilton CL, et al. (2007) Controlling the Scholl reaction. *J Org Chem* 72: 2279-2288.
10. Rempala P, Kroulák J, King BT (2006) Investigation of the mechanism of the intramolecular Scholl reaction of contiguous phenylbenzenes. *J Org Chem* 71: 5067-5081.
11. Kovacic P, Jones MB (1987) Dehydro coupling of aromatic nuclei by catalyst-oxidant systems: poly(p-phenylene). *Chem Rev* 87: 357-379.
12. Scholl R, Mansfeld J (1910) meso-Benzdianthron (Helianthron), meso-Naphthodianthron, und ein neuer Weg zum Flavanthron. *Ber Dtsch Chem Ges* 43: 1734-1746.
13. Kumar S (2006) Self-organization of disc-like molecules: chemical aspects. *Chem Soc Rev* 35: 83-109.
14. Kumar S (2012) Functional discotic liquid crystals. *Israel J Chem* 52: 820-829.
15. Kumar S (2011) Chemistry of discotic liquid crystals: from monomers to polymers. CRC Press, Boca Raton, FL.
16. Bushby RJ, Kawata K (2011) Liquid crystals that affected the world: discotic liquid crystals. *Liq Cryst* 38: 1415-1426.
17. Bisoyi HK, Kumar S (2011) Carbon-based liquid crystals: art and science. *Liq Cryst* 38: 1427-1449.
18. Kaafarani BR (2011) Discotic liquid crystals for opto-electronic applications. *Chem Mater* 23: 378-396.
19. Pisula W, Feng X, Mullen K (2011) Charge-carrier transporting graphene-type molecules. *Chem Mater* 23: 554-567.
20. Bisoyi HK, Kumar S (2010) Discotic nematic liquid crystals: science and technology. *Chem Soc Rev* 39: 264-285.
21. Kumar S (2009) Playing with discs. *Liq Cryst* 36: 607-638.
22. Goodby JW, Saez IM, Cowling SJ, GÁrtz V, Draper M, et al. (2008) Transmission and amplification of information and properties in nanostructured liquid crystals. *Angew Chem Int Ed Engl* 47: 2754-2787.
23. Wu J, Pisula W, Mullen K (2007) Graphenes as potential material for electronics. *Chem Rev* 107: 718-747.
24. Laschat S, Baro A, Steinke N, Giesselmann F, HÁgele C, et al. (2007) Discotic liquid crystals: from tailor-made synthesis to plastic electronics. *Angew Chem Int Ed Engl* 46: 4832-4887.
25. Sergeev S, Pisula W, Geerts YH (2007) Discotic liquid crystals: a new generation of organic semiconductors. *Chem Soc Rev* 36: 1902-1929.
26. Tschierske C (2007) Liquid crystal engineering--new complex mesophase structures and their relations to polymer morphologies, nanoscale patterning and crystal engineering. *Chem Soc Rev* 36: 1930-1970.
27. Kato T, Mizoshita N, Kishimoto K (2005) Functional liquid-crystalline assemblies: self-organized soft materials. *Angew Chem Int Ed Engl* 45: 38-68.
28. Donnio B, Guillon D, Deschenaux R, Bruce DW (2003) Comprehensive coordination chemistry II; McCleverty JA, Meyer TJ, Eds., Elsevier: Oxford, pp 357-627.
29. Ohta K, Hatsusaka K, Sugibayashi M, Ariyoshi M, Ban K, et al. (2003) Discotic liquid crystalline semiconductors. *Mol Cryst Liq Cryst* 397: 25-45.
30. Boden N, Bushby RJ, Clements J, Movaghar B (1999) Device applications of charge transport in discotic liquid crystals. *J Mater Chem* 9: 2081-2086.
31. Cammidge AN, Bushby RJ in *Handbook of Liquid Crystals*; Demus D, Goodby J, Gray GW, Spiess HW, Vill V, Eds. (1998) Wiley-VCH: Weinheim, Vol. 2B, Chapter VII, pp 693-748.
32. Heiner D, Lehmann M, Meier H (2010) Star-shaped conjugated systems. *Materials* 3: 3218-3330.
33. Imrie CT, Lu Z, Picken SJ, Yildirim Z (2007) Oligomeric rod-disc nematic liquid crystals. *Chem Commun (Camb)*: 1245-1247.
34. Kumar S (2005) Triphenylene-based discotic liquid crystal dimers, oligomers and polymers. *Liq Cryst* 32: 1089-1113.
35. Kumar S (2004) Recent developments in the chemistry of triphenylene-based discotic liquid crystals. *Liq Cryst* 31: 1037-1059.
36. Kouwer PH, Pourzand J, Mehl GH (2004) Disc-shaped triphenylenes in a smectic organisation. *Chem Commun (Camb)*: 66-67.
37. Bushby RJ, Lozman OR (2002) Photoconducting liquid crystals. *Current Opinion Solid State Mater Sci* 6: 569-578.
38. Matheson IM, Musgrave OC, Webster CJ (1965) Oxidation of veratrole by quinines. *J Chem Soc Chem Commun* 13: 278-279.
39. Boden N, Borner RC, Bushby RJ, Cammidge AN, Jesudason MV (1993) The synthesis of triphenylene-based discotic mesogens: new and improved routes. *Liq Cryst* 15: 851-858.
40. Kumar S, Manickam M (1997) Oxidative trimerization of o-dialkoxybenzeno-hexaalkoxytriphenylenes: molybdenum(v) chloride as a novel reagent. *Chem Commun* 1615-1666.
41. Kumar S, Varshney S (1999) Vanadium oxytrichloride, a novel reagent for the oxidative trimerization of o-dialkoxybenzenes to hexaalkoxytriphenylenes. *Liq Cryst* 26: 1841-1843.
42. Paquette LA, Crich D, Fuchs PL, Molander G (Eds.) (2009) *Encyclopedia of reagents for organic synthesis*. Wiley, West Sussex, UK.

Citation: Kumar S, Srinivasa HT (2013) Synthesis of Symmetrical and Unsymmetrical Triphenylene Discotic Liquid Crystals Using Antimony(V) Chloride Under Scholl Oxidation. *Organic Chem Curr Res* 2: 116. doi:10.4172/2161-0401.1000116

Submit your next manuscript and get advantages of OMICS Group submissions

Unique features:

- User friendly/feasible website-translation of your paper to 50 world's leading languages
- Audio Version of published paper
- Digital articles to share and explore

Special features:

- 250 Open Access Journals
- 20,000 editorial team
- 21 days rapid review process
- Quality and quick editorial, review and publication processing
- Indexing at PubMed (partial), Scopus, DOAJ, EBSCO, Index Copernicus and Google Scholar etc
- Sharing Option: Social Networking Enabled
- Authors, Reviewers and Editors rewarded with online Scientific Credits
- Better discount for your subsequent articles

Submit your manuscripts as E-mail: editor.organicchemistry@omicsonline.org